

Silicone Transfers



TECHNICAL DATASHEET

www.ja-int.com

APPLICATION

Temperature (°C): 150°C

Temperature (°F): 302°F

Time: 10 seconds

Pressure: Medium 42.7 - 56.9 psi / 2.9 - 3.9 bar / 3.0 - 4.0 kg/cm²

Carrier Release: Cold peel

Heat seal again for 5 seconds after removing the carrier

MATERIAL

155 micron silicone

LAUNDERING

Suitable for domestic wash up to 60°C

Can be tumble dried on the low setting

Ironable only inside out, on low heat

Do not dry-clean

Do not bleach

HANDLING AND STORAGE

Store in a damp-free environment at a stable temperature of ~20°C

Keep away from direct sunlight

No personal protection equipment is required in handling and storage

Do not attempt to apply any transfer that has been removed from its carrier